

Testing report

Testing description:

Tear testing according to ISO 34

Company:

Técnica Industrial Oswaldo Filizola Ltda.


Operator:

Tiago Ranalli

Date:

09/04/2009 15:19:24

Resultados do ensaio



Parameters by testing

	Testing 1	Testing 2	Testing 3	Testing 4
Thickness [mm]	2,000	2,000	2,000	2,000
Tear strength [N/mm]	3,310	3,187	3,236	3,408

Statistics among testings

	Average	Std Deviation	Variance	Median
Thickness [mm]	2,000	0,000	0,000	2,000
Tear strength [N/mm]	3,285	0,096	0,009	3,273

Statistics by testing

	Average	Std deviation	Variance	Median
Testing 1	5,676	1,987	3,948	6,521
Testing 2	5,612	1,630	2,658	6,203
Testing 3	5,657	1,704	2,905	6,423
Testing 4	6,105	1,777	3,157	6,767

Remarks:

Sample manufactured on 13/02/2009 /Test piece type: Nitrile rubber 70 Shore

Remarks:

Temperature of test: 24°C

DynaView ©2005 - 2009